

37-208180/30 A93 E12 I02 (E34) INCE-09.05.85 A(10-E9B, 12-R1A) E(33-C) I(2-D3)

INCERC INST CERCETA

09.05.85-HU-001755 (29.06.87) C04b-38/10

Light concrete - comprises foaming agent of laurate-sodium sulphate and PVA alcohol in aq. soln. sodium hexa-metaphosphate and calcium stearate
C87-087150

0.04% of an active foaming agent, comprising a 20% soln. of (%w/w) 20 laurate-sodium-sulphate and 1 polyvinyl alcohol is mixed in the cement mixt. together with 1% sodium hexametaphosphate and 1% calcium stearate. The prod. has a 16% porosity, approx. density of 1800 kg/m³ and compression strength of 120 daN/cm².

37-208180/30 A92-041-A INCE-09.05.85 HU T042-041-A

DERWENT PUBLICATIONS LTD.